

材料暨工程實驗室-高雄

試驗報告

報告編號: KV-19-03235

數: 1 OF 報告日期:108年 05月 13日

委託單位:善群實業有限公司 產品名稱:壓克力彈性水泥

產品型號: AC-009MS

送驗廠商:善群實業有限公司 收件日期: 108年 04月 22日

試驗日期: 108年 04月 22日~108年 05月 13日

註: 1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

試驗結果:

試驗項目	77. 644. 44	試驗方法	試驗結果
抗拉強度(kgf/cm²)		参照 CNS 3553(1996) (3 號形試片,V=500mm/min)	63.7
撕裂強度(kgf/cm)		参照 CNS 3559(2007) (C 形試片,V=500mm/min)	35.3
接著強度(kgf/cm²) (試驗底材:混凝土)	標準狀態	参照 CNS 8082(2010)	29.0

註:試驗樣品為單液型。

---- 000 -----

本報告若有提供規範值,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonetate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWC 6 8 3 1 3 3 4

SGS Taiwen Ltd. 台灣檢驗科技股份有限公司 | t (886-7) 301-2121

No.6.1, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號 www.sgs.tw f (886-7) 301-1165