

## 試驗報告



報告編號：KV-21-09324

頁數：1 OF 1

報告日期：110年11月09日

委託單位: 善群實業有限公司，貴宏興業股份有限公司  
 樣品名稱: 環氧樹脂填縫材料  
 送驗人員: 善群實業有限公司，貴宏興業股份有限公司(周信樺)  
 收件日期: 110年10月19日  
 試驗日期: 110年10月19日~110年11月09日

- 備註: 1. 以上資料由顧客提供(收件及試驗日期除外)  
 2. 除非另有說明，此報告結果僅對測試之樣品負責  
 未經本公司事先書面同意，此報告不可部分複製  
 3. 下述報告內容標示#處由顧客提供

### 試驗結果:

試驗項目	試驗方法	試驗結果
抗壓強度(kgf/cm <sup>2</sup> )	ASTM D695-15	729
抗拉強度(kgf/cm <sup>2</sup> )	ASTM D638-14 (Type I, V = 5 mm/min.)	288
抗彎強度(kgf/cm <sup>2</sup> )	ASTM D790-17 Procedure AI	485

註: 1. #試驗樣品之配比 = A劑 : B劑 = 1 : 1 (重量比)。

2. 本試驗報告之試驗地點同實驗室地址。

----- oOo -----

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準

陳秉豐  
報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.