



## 試驗報

報告編號: KV-18-04628

數: 1 OF

報告日期:107年 05月 31日

委託單位: 善群實業有限公司

產品名稱:三組份抗劃傷透明面塗 收件日期: 107年 05月 21日

試驗日期: 107年 05月 21日~107年 05月 30日

註: 1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

試驗項目	試驗方法	試驗結果
鉛筆硬度		A process of the control of the cont
刮傷法	CNS 10757(1995)	H
破損法		9H
耐磨耗性(mg)		114.5
(CS-10, 1000 g, 1000 轉)		
耐化學性(滴定, 24 h)	参照 CNS 4447(1992)	Islantina a concentration and account of
10% 硝酸		目視外觀無失去光澤、褪色、模糊、龜裂、膨潤、 彎曲、分解、溶解、黏著、起泡
20% 硫酸		目視外觀無失去光澤、褪色、模糊、龜裂、膨潤、 彎曲、分解、溶解、黏著、起泡
20% 鹽酸		目視外觀無失去光澤、褪色、模糊、龜裂、膨潤、 彎曲、分解、溶解、黏著、起泡
30% 氫氧化鈉		目視外觀無失去光澤、褪色、模糊、龜裂、膨潤、 彎曲、分解、溶解、黏著、起泡

註:1.試驗試片由委託單位製備提供。

2.本試驗報告耐化學性試驗非 TAF 認證範圍,其餘則非。

本報告若有提供規範值,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx">http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx</a>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.