

Testing Laboratory 0526

材料暨工程實驗室-高雄

試驗報告

報告編號: KV-20-01096

數: 1 OF 報告日期:109年 03月 10日

善群實業有限公司

產品名稱: 無溶劑型薄塗面漆 送驗廠商:善群實業有限公司 收件日期: 109年 02月 14日

試驗日期: 109年 02月 14日~109年 03月 09日

註: 1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

試驗結果:

試驗項目	試驗方法	試驗結果
鉛筆硬度(刮傷法)	CNS 10757(1995)	Н
鉛筆硬度(破損法)		9H
附著強度(kgf/cm²) 底材:混凝土	参照 CNS 10757(1995)	25.9
耐磨耗性(mg) (CS-10, 1000 g, 1000 轉)	CNS 10757(1995)	36.8

註:1.主劑:硬化劑重量比=5:1由委託單位提供。

- 2.依委託單位指定,附著強度試片底材使用混凝土。
- 3.本試驗報告附著強度試驗非 TAF 認證範圍,其餘則是。
- 4.本試驗報告之試驗地點同實驗室地址。

---- 0 0 0 -----

本報告若有提供規範值,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWC8802208