

試驗報告



報告編號：KV-22-04698

頁數：1 OF 1

報告日期：111年07月29日

善群實業有限公司，貴宏興業股份有限公司

產品名稱：水性環氧壁塗

送驗廠商：善群實業有限公司，貴宏興業股份有限公司

收件日期：111年06月23日

試驗日期：111年06月23日~111年07月29日

備註：1.以上資料(產品名稱、送驗廠商、收件日期及試驗日期除外)及下述報告內容
標示#處係由顧客提供
2.除非另有說明，此報告結果僅對測試之樣品負責
未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
抗初期乾燥龜裂性	CNS 8082(2021)	無龜裂
附著強度(標準狀態)(N/mm ²)		2.3
耐磨耗性(1000次)		無剝離及磨耗所引起之露出底材
耐鹼性B法 (溫度(23±2)°C,相對溼度(50±5)%, 72 h)	CNS 8082(2010)	無龜裂、剝離、膨脹、皺紋、變色及光澤之變化
耐濕性 (23 °C水中 / 60min. → 60 ± 5 °C / 24 h)		無龜裂、剝落、膨脹、皺紋、變色及光澤變化

- 註：1.#試驗配比(重量比)主劑：硬化劑=11：1。
2.#抗初期乾燥龜裂性試驗之塗布量為 0.1 kg/m²。
3.本試驗報告抗初期乾燥龜裂性試驗委託台灣塗料工業同業公會研究發展檢驗室執行 (TAF 認證編號：1376)。
4.本試驗報告抗初期乾燥龜裂性、附著強度試驗為 TAF 認證範圍，其餘則非。
5.本試驗報告之試驗地點同實驗室地址。

----- oOo -----

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.